



GRAPHITE BLANKS, PLATES, SHEETS, BLOCKS



GRAPHITE ROUNDS, TUBES, HEXES



GRAPHITE TAPS



GRAPHITE CNC MACHINING



METALLIC ELECTRODES




EDM TUBES

MATERIALS CHART

Grade	Application	Grain	Avg. Particle Size (In.)	Apparent Density g/cm ³	Shore Hardness	Electrical Resistance μΩ-in.	Flexural Strength psi	Compressive Strength psi
AR-6	EDM	Fine	0.00047	1.78	55	539	6,500	14,300
AR-8	EDM	Fine	0.00047	1.80	65	488	7,500	16,500
AR-12	EDM	Super-Fine	0.00035	1.82	65	450	8,400	18,400
AR-200	EDM	Super-Fine	0.00028	1.78	60	500	8,700	17,110
AR-14	EDM	Ultra-Fine	0.00019	1.86	80	500	11,000	24,200
TTK-4	EDM	Ultra-Fine	0.00016	1.78	72	552	10,600	19,600
DS-4	EDM	Ultra-Fine	0.00016	1.88	72	500	13,050	27,250
DS-4C	EDM	Ultra-Fine	0.00016	3.00	75	150	19,000	28,000
EDM-1®	EDM	Ultra-Fine	0.00019	N/A	69	760	9,700	14,200
EDM-3®	EDM	Ultra-Fine	0.00019	N/A	73	615	13,300	18,100
EDM-C3®	EDM	Ultra-Fine	0.00019	N/A	66	127	20,300	28,350
EDM-AF5®	EDM	Angstro-Fine	0.00004	N/A	83	850	14,500	22,100
CC-1940	Mechanical	Fine	0.00051	1.79	63	520	6,300	13,000
JP-1300	Mechanical	Fine	0.00063	1.72	72	1,000	8,400	24,000
UT-3	Mechanical	Fine	0.00169	1.78	60	453	5,800	11,000
UT-2E	Mechanical	Coarse	0.03150	1.72	40	315	2,400	5,100

Specifications are typical from manufacturer & subject to minor changes

QUICK-CHANGE ELECTRODES



Quick change is easier with our Erowa and 3R Graphimator® options.

Contact us for immediate pricing!

Toll free: **800-448-8887**

E-mail: info@ohiocarbonblank.com

Instant quotes with our Online Catalog: www.ohiocarbonblank.com



Ohio Carbon Blank, Inc.
38403 Pelton Road,
Willoughby, OH 44094

800-448-8887
440-953-9302
440-953-5829

toll free
local
fax

www.ohiocarbonblank.com
info@ohiocarbonblank.com